

THERMAL PAD

CHM250

High thermal conductivity pads are developed for applications requiring moderate thermal resistance.



Typical Properties	
Colour	Black
Base Polymer	Acryl
Tensile Strength (MPa)	> 3.0
Thickness (mm)	0.2, 0.3, 0.5, 1.0, 2.0
Hardness Shore A	92
Standard Size (mm)	210 x 297
Dielectric Breakdown Voltage (kV)	> 0.255
Applicable Frequency	100 MHz ~ 6 GHz
Temperature Range (°C)	- 40 ~ 130
Flammability Level	94V-0
Thermal Conductivity (W/m.K)	2.4

AMEC Thermasol

Marcom House, 1-2 Steam Mill Lane, Great Yarmouth, Norfolk, NR31 0HP

Telephone: +44(0) 1493 668622 Fax: +44(0) 1493 668623

Email: sales@amecthermasol.co.uk Website: www.amecthermasol.co.uk