

THERMAL PAD

ATS050

High thermal conductivity pads are developed for applications requiring moderate thermal resistance.



Typical Properties	
Colour	Grey
Thickness (mm)	0.3 ~ 18
Tensile Strength (kg/cm ²)	1.45
Elongation (%)	80
Hardness Shore A	20
Specific Gravity (g/cm ³)	2.45
Insulation Strength (Volt/mm)	1,000
Weight Loss @ 204°C / 24hrs	<1
Temperature Range (°C)	-60 ~ +150
Flammability Level	94V-0
Thermal Conductivity (W/m.K)	5.00

AMEC Thermasol

1-2 Steam Mill Lane, Great Yarmouth, Norfolk, NR31 0HP

Telephone: +44(0) 1493 668622 **Fax:** +44(0) 1493 668623

Email: sales@amecthermasol.co.uk **Website:** www.amecthermasol.co.uk