



FGS-0065

Tech Index:

ITEMS	UNITE	STANDARD	DATA
Carbon content	%	≥98	99.5
Thickness tolerance	mm	0.065±0.005	0.065±0.005
Density tolerance	g/cm ³	1.6±0.05	1.6±0.05
Sulphur content	PPM	≤1200	800
Thermal conductivity through plane	W/MK	750 (for reference only)	
Thermal conductivity through thickness	W/MK	8 (for reference only)	
Remark	According : JB/T 7758.2-2005, ASTM D5470		

AMEC Thermasol

1-2 Steam Mill Lane, Great Yarmouth, Norfolk, NR31 0HP

Telephone: +44(0) 1493 668622

Fax: +44(0) 1493 668623

Email: sales@amecthermasol.co.uk

Website: www.amecthermasol.co.uk